

PLASTUB® PEBD

LDPE tube 49 Shore D
Food grade translucent



Description

Low-density polyethylene extruded tube

Applications

Pressurised transport of compressed air, chemical products, gas, lubricant

Fields

Maintenance, control, process, instrumentation

General characteristics

- Lightweight
- Small bend radius
- Physiologically inert
- Food grade
- Very good chemical resistance

Technical data

- Standard: * FDA-approved material: 21 CFR 177.1520, European regulations 1935/2004, 10/2011 and 2023/2006
- Temperature of use: -15 to +50°C
- Nominal hardness: **49 Shore D** as per ISO R 868
- Nominal density: 0.92 as per ISO 1183
 - Tensile strength: >12 Mpa as per ISO R 527
 - Elongation at break: >500 % as per ISO R 527
- Standard colour: translucent
- Recommended connection: compression tube fittings

Options (contact us)

- Other diameters
- Other solid colours
 - Cut to lengths
- Other packaging
- Surface marking
- Sheathed versions

Nominal internal diameter (mm)	Nominal outside diameter (mm)	Bending radius* (mm)	Operating pressure* (bar)	Burst pressure* (bar)	Nominal linear weight (g/m)	Standard packaging	
						Roll (m)	Drum (m)
2	4	19	21	72	9	100	500
4	6	31	13	42	14	100	500
6	8	42	10	32	20	100	500
8	10	68	6	19	26	100	500
10	12	100	5	16	32	100	-

Coefficient applicable to operating temperature according to the temperature

+20°C	+30°C	+50°C
100%	83%	64%

Standard tolerances: refer to pages 115 to 118.

*Values provided for information purposes for an ambient temperature of 23°C.



Zone Industrielle 63600 AMBERT - France

Tel. + 33 (0)4 73 82 44 36

e-mail: plastub@omerin.com

www.plastub.fr

The information given in this technical data sheet is indicative and subject to change without prior notice. As the conditions of use and the environment in which the product is used cannot be fully covered in our design work, PLASTUB shall not assume liability for any incidents in the event of inappropriate use and/or not carried out according to best practices and applicable standards.

To ensure optimal use of our products, we recommend full tests in real-life situations.

To this end, our sales department is on hand to supply samples and/or to examine the conditions of comprehensive testing in our laboratories.

© Registered trademark of PLASTUB. Drawings and photos are not contractual. Reproduction is prohibited without the prior agreement of PLASTUB.